



# ELM<sup>®</sup> rHDPE-80

Recycled High Density Polyethylene Compound

## APPLICATION

Extrusion, injection moulding, blow moulding

Physical Properties	Typical Value	Method
Density (23°C)	0.94 - 0.96 g/cm <sup>3</sup>	ISO 1183
Melt Flow Index (190°C/5 kg)	1.5 - 2.0 g/10 min	ISO 1133
Ash Content	≤ 3 %	ISO 3451
Form	3 - 5 mm granules	
Color Options	Black, Blue, Green	

## STORAGE

This product should be stored in a dry area with an ambient temperature below 50°C. It should be kept away from sunlight and heat. Inappropriate storage conditions can lead to deterioration in physical properties. It is advised to process pellets within 12 months after delivery.

## PACKAGING

The product is packed in 1200 kg Big Bags.

## NOTES

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests. Please contact for product samples.