



**Data Sheet** Date Prepared:

## **HDPE 8800**

 $\Upsilon$ UZEX 8800 provides stronger film than ones made from competitive HDPE film grades and this grade is bimodal type resin. Therefore "YUZEX" 8800 shows superior stability in film extrusion to that of competitive HDPE film resins and gives excellent appearance to its film. YUZEX 8800 has ultra high molecular weight polymer and this make excellent mechanical properties compared with competitive HDPE film grades.

### **Application / Use Case**

Film / agriculture, industrial, shopping bags, trash bags

#### Characteristic

Tearing strength, Impact strength

# Specification

	Specification	Unit	Test Method	
Density	0.956	g/cm <sup>3</sup>	ASTM D1505	
Melt Index	0.048	g/10min	ASTM D1238	

#### **Physical Properties**

	Value	Unit	Test Method
Softening Point(Vicat)	124	°C	ASTM D 1525
Tensile Strength at Yield	230	kg/cm <sup>2</sup>	ASTM D638
Tensile Strength at Break	300	kg/cm <sup>2</sup>	ASTM D638
Elongation at Break	>500	%	ASTM D638
IZOD Impact Strength(Notched, 23°C)	NB	kg cm/cm	ASTM D256
Flexural Modulus	10000	kg/cm <sup>2</sup>	ASTM D790
ESCR	>600	hr	ASTM D1693

These are typical properties only, and are not to be construed as specific limits.

**Head Office** 99 Seorin-dong, Jongno-gu, Seoul 110-110, Korea

Tel. 82-2-2121-5114 Fax. 82-2-2121-7001

SK Institute of 140-1 Woncheon-dong, Yuseong-gu, Taejeon, Korea Technology Tel. 82-42-866-7624 Fax. 82-42-866-7603

Online www.skglobalchemical.com

www.skchem.com

ISO 9001 Certified