

elm kimyo

Formosa Plastics[®] Formolene[®] FR2233C

Fractional Melt LDPE Resin with no Slip or Antiblock

Formolene® FR2233C is a low density polyethylene with film exhibiting medium optical properties.

Formolene® FR2233C is formulated without slip and antiblock for use in high performance film applications offering excellent extrusion processing and outstanding melt strength characteristics suitable for thick film gauges and large layflat widths.

Suggested Applications:

Tensile Strength at Break

Elongation at Break

Secant Modulus @ 1%

Construction Film Pallet Shrink	Heavy Duty Bags Pallet Shrink Film High Performance Collation Sl		Foams Profile Extrusion	
Nominal Physical Properties:				
	TEST			
PROPERTY	METHOD	UNIT	VALUE	
Density	D1505	g/cc	0.922	
Melt Index, Condition E, 190°C/2.16 kg	D1238	g/10 min	0.33	
Dart Impact	D1709	g	490	
Elmendorf Tear Strength	D1922	g	260/460*	
Tensile Strength at Yield	D882	psi	1800/1700*	

Note: Film properties based on 5.9 mil (150 micron) thick film produced using a 7.9 inch (200 mm) die and 39.4 mil (1.0 mm) die
gap with a 1.5:1 Blow-Up Ratio and temperature profile of 293 - 374°F (145 - 190°C). Actual film properties may vary based on
extrusion equipment, operating conditions and additive package. Film properties are not intended to be used as specifications.

D882

D882

D882

D2457

D1003

psi

%

psi

%

2900/2500*

280/540*

33000/41000*

45

15.0

Published 07/15/19

Gloss (45°)

* MD / TD

Haze

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (800) 363-1823 • Fax: (973) 716-7483

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. The information and recommendations in this publication are, to the best of our Moviege, reliable, Suggestions concerning uses or applications are only the ophinon of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the usuability of these products for their own particular purposes. However, because of numerous factors affecting the results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. The responsibility of FORMOSA PLASTICS CORPORATION, U.S.A. for fairfingement of warrant, resplicance, strict is ability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.