

# ADVANCENE™ EE-1802-AAH

## Linear Low Density Polyethylene

### Overview:

ADVANCENE™ EE-1802-AAH is a Linear Low Density Polyethylene Resin is an ethylene-hexene-1 copolymer designed for cast stretch film applications such as industrial pallet wrap. Films containing EE-1802-AAH offer outstanding toughness and load holding properties.

### Main Characteristics:

- Industrial pallet wrap stretch film applications
- Premium film packaging applications

Physical	Typical Value (SI)	Test Method
Density	0.918 g/cm <sup>3</sup>	ASTM D792
Melt Index (190 °C/2.16 Kg)	2 g/10 min	ASTM D1238, ISO 1133
Film Properties	Typical Value (SI)	Test Method
<b>Film Puncture Energy</b>		
0.80 mil (20 µm)	4.29 J	UNIVATION Method
2.0 mil (51 µm)	8.81 J	
<b>Film Puncture Force</b>		
0.80 mil (20 µm)	44.5 N	UNIVATION Method
2.0 mil (51 µm)	89 N	
<b>Film Puncture Resistance</b>		
0.80 mil (20 µm)	30.8 J/cm <sup>3</sup>	UNIVATION Method
2.0 mil (51 µm)	24.0 J/cm <sup>3</sup>	
<b>Film Toughness</b>		
MD: 0.80 mil (20 µm)	203 J/cm <sup>3</sup>	ASTM D882
MD: 2.0 mil (51 µm)	225 J/cm <sup>3</sup>	
TD: 0.80 mil (20 µm)	358 J/cm <sup>3</sup>	
TD: 2.0 mil (51 µm)	262 J/cm <sup>3</sup>	
<b>Secant Modulus</b>		
2% Secant, MD: 0.80 mil (20 µm)	142 MPa	ASTM D882
2% Secant, MD: 2.0 mil (51 µm)	138 MPa	
2% secant, TD: 0.80 mil (20 µm)	150 MPa	
2% secant, TD: 2.0 mil (51 µm)	138 MPa	

<b>Tensile Strength</b> MD: Yield, 0.80 mil (20 µm) MD: Yield, 2.0 mil (51 µm) TD: Yield, 0.80 mil (20 µm) TD: Yield, 2.0 mil (51 µm) MD: Break, 0.80 mil (20 µm) MD: Break, 2.0 mil (51 µm) TD: Break, 0.80 mil (20 µm) TD: Break, 2.0 mil (51 µm)	10.6 MPa 9.8 MPa 11.3 MPa 10.3 MPa 55.7 MPa 38.4 MPa 47.2 MPa 37.5 MPa	ASTM D882
<b>Tensile Elongation</b> MD: Break, 0.80 mil (20 µm) MD: Break, 2.0 mil (51 µm) TD: Break, 0.80 mil (20 µm) TD: Break, 2.0 mil (51 µm)	480 % 700 % 890 % 800 %	ASTM D882
<b>Dart Drop Impact</b> 0.80 mil (20 µm) 0.80 mil (20 µm) 2.0 mil (51 µm) 2.0 mil (51 µm)	130 g < 100 g 330 g 210 g	ASTM D1709A ASTM D1709B ASTM D1709A ASTM D1709B
<b>Elmendorf Tear Strength</b> MD: 0.80 mil (20 µm) MD: 2.0 mil (51 µm) TD: 0.80 mil (20 µm) TD: 2.0 mil (51 µm)	220 g 790 g 640 g 1100 g	ASTM D1922 <sup>1</sup>
<b>Ultimate Stretch</b> 0.8 mil (20 µm) 2.0 mil (51 µm) <b>Ultimate Stretch</b> 0.8 mil (20 µm) 2.0 mil (51 µm)	300 % 470 % 220 g 310 g	UNIVATION Method <sup>2</sup>
<b>Thermal</b>	<b>Typical Value (SI)</b>	<b>Test Method</b>
Vicat Softening Temperature	98.9 °C	ASTM D1525
Melting Temperature (DSC)	123 °C	UNIVATION Method
<b>Optical</b>	<b>Typical Value (SI)</b>	<b>Test Method</b>
Gloss 20°, 0.8 mil (20 µm) 20°, 2.0 mil (51 µm) 45°, 0.8 mil (20 µm) 45°, 2.0 mil (51 µm)	157 149 95 91	ASTM D2457

Haze		
0.8 mil (20 µm)	1.0 %	ASTM D1003
2.0 mil (51 µm)	3.0 %	
<b>Extrusion</b>		
Melt Temperature	274 °C	

### Extrusion Notes

Fabrication Conditions for Cast Film:

- Egan/ Davis-Standard 5-layer cast line
- Melt Temperature: 525°F (274°C)
- Chill Roll (primary/ secondary) Temperature: 70°F (21°C)
- Line Speed: 600 fpm (183 m/Min) for 0.8 mil; 200 fpm (61 m/min) for 2.0 mil
- Output: 401 lb/hr (180 kg/hr) for 0.8 mil; 340 lb/hr (150 kg/hr) for 2.0 mil
- Die width: 36 in (914 mm)
- Die Gap: 25 mil (0.65 mm)
- Air gap: 3 in (76 mm)

### Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

1 Method B

2 On-Pallet Testing; Highlight Industries Inc. test method.

### Availability:

This product is supplied in 25 kg bags in secured pallets of 60 bags (1.500 MT net).

It is also supplied in jumbo bags of 1000 kg capacity.

### Storage:

The product should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage can be found in Safety Information Sheet for this product.

### Safety:

The product is not classified as a hazardous mixture.

Dust and fines from the product carry a risk of dust explosion. All equipment should be properly earthed. Inhalation of dust should be avoided as it may cause irritation of the respiratory system. Small amounts of fumes are generated during processing of the product. Proper ventilation is therefore required.

A Safety Information Sheet is available on request. Please contact your ETHYDCO representative for more details on various aspects of safety, recovery and disposal of the product.

**Recycling:**

The product is suitable for recycling using modern methods of shredding and cleaning.

In-house production waste should be kept clean to facilitate direct recycling.

**Related Documents:**

Most datasheets and statements are available on ETHYDCO website [www.ethydc0-eg.com](http://www.ethydc0-eg.com). If more information is required, please contact a ETHYDCO representative for information.

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

**Disclaimer**

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however, we do not assume any liability whatsoever for the accuracy and completeness of such information.

ETHYDCO makes no warranties, which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of ETHYDCO's products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

**ADVANCENE is a trademark of ETHYDCO.**