



TOPILENE R200P

Properties of Topilene R200P				
Category	Test Method	Unit	R200P	
			(Random PP)	
Melt Index	ASTM D792	g/10min	0.2	
Melting Temp	HS Method	°C	140	
Tensile Strength	(at Yield)	(at Break)	270	
	(at Break)		230	
Elongation	ASTM D638	%	500	
Flexural Modulus	ASTM D790	Kg/cm ²	8,5	
Izod Impact Strength	ASTM D256	Kg-cm/cm	No Break	
			23°C	8
			0°C	3
			-20°C	

Material : Polypropylene Random Copolymer

Durability : 50 yrs

Construction : Satisfactory

Connection : Heat fusion

Corrosion : None

Recycling : Possible

Major function : Cold and hot water supplying pipes/ Under floor heating pipes/ Chemical pipes