



**EGYPTIAN PETROCHEMICALS CO.**

**PVC RESIN K- VALUE 67  
SPECIFICATIONS**

		SPECIFICATION
<b>I.V</b>		<b>0.90-0.94</b>
<b>POROSITY</b>	<b>ml/gm</b>	<b>0.20-0.32</b>
<b>A.B.D</b>	<b>gm/ml</b>	<b>0.49-0.56</b>
<b>PARTICAL SIZE</b>	<b>RET40</b> %max	<b>1</b>
	<b>RET60</b> %max	<b>5</b>
	<b>TH.140</b> %max	<b>25</b>
<b>A.P.S</b>	<b>MICRON</b>	<b>150-170</b>
<b>H.L</b>	<b>%max</b>	<b>0.3</b>
<b>D.R</b>	<b>/100 INCH<sup>2</sup> MAX.</b>	<b>6</b>
<b>F.E</b>	<b>/36 INCH<sup>2</sup> MAX.</b>	<b>20</b>
<b>F.T</b>	<b>SEC.</b>	<b>15-25</b>
<b>R.VCM</b>	<b>PPM max.</b>	<b>1</b>

\*The data in this leaflet are given to the best of our knowledge . The suitability of the products or material has to be determined by the user & all safety precautions have to be taken by himself. We make no warranty or guarantee as to the results using these products since the use of these products is not under EPC control .



**EGYPTIAN PETROCHEMICALS CO.**

Km 36 Alex/Cairo Desert Road Amreyia, Alex - Egypt

FAX: 00203 4770029 TEL: 00203 4770012 - 19

E-mail: epc@egy-petrochem.com

Web site: www.egy-petrochem.com

